

# FINON®

Style	Weight (oz/yd <sup>2</sup> )	Thickness (mils)	Air Perm (cfm/ft <sup>2</sup> )	Mullen Burst (psi)	Grab Tensile (MD/CD, lbf)
C3019 NW	0.55	2	627	20	12/7
C303 NW	0.90	5	530	24	22/20
C305 NW	1.50	6	300	45	38/34
C306 NW	1.80	8	250	50	60/48
C307 NW	2.10	9	180	60	72/66
C310 NW	2.95	11	100	130	91/47
L220 NW	6.00	22	55	175	100+/100+
L227 NW	8.00	23	30	300+	100+/100+

*These are typical values and not intended as specifications.  
Finon® is a registered trademark of Kolon.*

*Finon® is a unique performance oriented spunbond polyester media with these distinguishing characteristics:*

- Pattern bonded continuous fiber
- High strength to weight ratio
- Contains no chemical binder - all 100% polyester
- Excellent pleatability and thermal moldability
- Good abrasion resistance and durability
- Excellent dimensional stability - Good thermal resistance
- Does not ravel or fray