

LUTRADUR®

Style	Weight		Thickness (mils)	Air Perm (cfm/ft ²)	Mullen Burst (psi)	Grab Tensile (MD/CD, lbf)
	(g/m ²)	(oz/yd ²)				
LD-7240	40	1.12	8	970	50	30/30
LD-7250	50	1.50	9	840	60	39/38
LD-7270	70	2.10	10	540	72	58/58
LD-7210	100	2.90	17	495	120	107/87

*These are typical values and not intended as specifications.
Lutradur™ is a registered trademark of Freudenberg Spunweb Company.*

Lutradur™ is a unique performance oriented spunbond polyester media with these distinguishing characteristics:

- Spunbond continuous filament fiber sheet
- High strength to weight ratio
- No chemical binder - 100% Polyester
- Excellent pleatability and thermal moldability
- Low shrinkage
- Excellent dimensional stability
- Does not ravel or fray
- Coarse fiber for high flow rates