

CEREX

Style	Weight (oz/yd ²)	Thickness (mils)	Air Perm (cfm/ft ²)	Mullen Burst (psi)	Grab Tensile (MD/CD, lbf)
CEREX 30	0.3	3.0	1974	10	8/4
CEREX 40	0.4	3.0	1495	13	12/7
CEREX 50	0.5	3.7	1179	16	16/9
CEREX 60	0.6	3.9	981	20	20/12
CEREX 70	0.7	3.8	800	24	24/15
CEREX 85	0.85	4.0	632	29	31/20
CEREX 100	1.0	5.4	511	35	37/24
CEREX 150	1.5	6.9	292	53	59/39
CEREX 200	2.0	8.3	189	71	85/58

This data is intended only as a guide based upon statistical sampling of production runs

Cerex® is a unique performance oriented spunbond nylon media with these distinguishing characteristics:

- Unique fiber spinning process results in high degree of web uniformity
- Wide range of basis weights makes it ideally suited for economical filtration
- High tensile and tear strength even at low basis weights
- Continuous filaments prevent fiber migration
- Thermal stability with a melting point of up to 500°F
- Resists attack by many solvents, alkalis, and dilute acids

Cerex® is a registered trademark of Cerex Advanced Fabrics, L.P.